## NOTES:

- 1. SUBSTRATE: FUSED SILICA
- 2. COATING (APPLY ACROSS CLEAR APERTURE)

S1: NONE

S2: 352nm Laser AR Coating

R(ABS) < 0.25% @ 355nm @ 0° AOI


DAMAGE THRESHOLD


PULSED: 7.5J/cm<sup>2</sup> @ 20ns, 20Hz @ 355nm



3 FINE GRIND SURFACE

4. ROHS COMPLIANT





## FOR INFORMATION ONL DO NOT MANUFACTURE PARTS TO THIS DRAWING

SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

REV. A	\$1	\$2	
SHAPE	PLANO	PLANO	
SURFACE QUALITY	20-10	20-10	
CLEAR APERTURE	25.45 x 18.00	Ø18.00	
SURFACE FLATNESS	λ/20	λ/20	
BEVEL	PROTECTIVE AS NEEDED	PROTECTIVE AS NEEDED	

			<b>Edmund Optics®</b>		
	THIRD ANGLE PROJECTION		TITLE	20mm 1/20 WV 355nm AR CTD HT RA FS	PRISM
)	ALL DIMS IN	mm	DWG NO	37626	SHEET 1 OF 1

**(a)**