## NOTES:


- 1. SUBSTRATE: Fused Silica 458/678
- 2. ROHS COMPLIANT
- 3. CENTERING TOLERANCE (AT 587.6nm):
  BEAM DEVIATION (HALF ANGLE): <1 ARCMIN
- 4. COATING (APPLY ACROSS COATING APERTURE)


\$1 & \$2: 266nm Laser AR Coating R(ABS) < 0.25% @ 266nm @ 0° AOI

DAMAGE THRESHOLD PULSED: 3J/cm² @ 20ns, 20Hz @ 266nm



- 6. POWER, IRREGULARITY, AND SURFACE QUALITY SPECIFICATIONS APPLY ACROSS CLEAR APERTURE
- 7. FOCAL LENGTH (EFL): 300.00mm±1% BACK FOCAL LENGTH (BFL): 297.38mm
- 8. PROTECTIVE BEVEL AS NEEDED
- 9. DESIGN WAVELENGTH: 355nm





**SECTION A-A** 

## FOR INFORMATION ONLY: DO NOT MANUFACTURE PARTS TO THIS DRAWING

	\$1	\$2			
SHAPE	CONVEX	PLANO			
RADIUS	142.83	INFINITY			
SURFACE QUALITY	10 - 5	10 - 5			
MIN CLEAR APERTURE	Ø11.70	Ø11.70			
MIN COATING APERTURE	Ø11.70	Ø11.70			
POWER AT 632.8nm	2.00 RINGS	2.00 RINGS			
IRREGULARITY AT 632.8nm	0.20 RINGS	0.20 RINGS			

SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

		<b>Control</b> Edmund Opt		
THIRD ANG PROJECTIO	LE ————————————————————————————————————	TITLE	12.7mm Dia x 300mm FL, 266nm Laser AR Coating, 3J Coated, Plano-Convex Lens	
ALL DIMS IN	mm	DWG NO	38668	SHEET 1 OF 1